

Data Sheet

The Carrington Collection

Series of Premium Vinyl Siding



Illustration	Description/Packaging	Colors/Color Nos.			
<p>25D4</p>	Double 4" Length 12'-6" 12 Panels/Carton 1 Sq./Carton Carton Weight: 65 lbs.	Woodland Series English Walnut (72) Timber Wolfe (74) Whispering Pine (76) Harvest Brown (78)	Legacy Series Canyon Brown (81) Charcoal Grey (84) Heritage Red (87) Countryside Green (88) Hampton Blue (89)	Traditional Series White Birch (02) Classic Sand (11) Warm Sandalwood (17) Sunny Maize (22) Summer Wheat (26)	Dove Gray (40) Harbor Stone (44) Vintage Sage (55) Adobe Clay (60) Wicker Beige (65) Victorian Slate (67)

Illustration	Description/Packaging	Colors/Color Nos.			
<p>25DL5</p>	5" Dutch Lap Length 12' 10 Panels/Carton 1 Sq./Carton Carton Weight: 65 lbs.	Woodland Series English Walnut (72) Timber Wolfe (74) Whispering Pine (76) Harvest Brown (78)	Legacy Series Canyon Brown (81) Charcoal Grey (84) Heritage Red (87) Countryside Green (88) Hampton Blue (89)	Traditional Series White Birch (02) Classic Sand (11) Warm Sandalwood (17) Sunny Maize (22) Summer Wheat (26)	Dove Gray (40) Harbor Stone (44) Vintage Sage (55) Adobe Clay (60) Wicker Beige (65) Victorian Slate (67)

Illustration	Description/Packaging	Colors/Color Nos.			
<p>25D6</p>	6" Double ** Length 12.5' 8 Panels/Carton 1 Sq./Carton Carton Weight: 65 lbs.	Woodland Series English Walnut (72) Timber Wolfe (74) Whispering Pine (76) Harvest Brown (78)	Legacy Series Canyon Brown (81) Charcoal Grey (84) Heritage Red (87) Countryside Green (88) Hampton Blue (89)	Traditional Series White Birch (02) Classic Sand (11) Warm Sandalwood (17) Sunny Maize (22) Summer Wheat (26)	Dove Gray (40) Harbor Stone (44) Vintage Sage (55) Adobe Clay (60) Wicker Beige (65) Victorian Slate (67)

Carrington Collection™ Premium Vinyl Siding

Styles and accessories to fit your most exacting need.



1411 Majestic Drive
 P.O. Box 690
 Fremont, OH 43420

Product Test Data

Thickness.....	048" ± .001"
Specific Gravity.....	1.45
Tensile Strength (PSI).....	7,154
Tensile Modulus (PSI).....	416,900
IZOD Impact Strength @ 32°F.....	Passes per ASTM D3679
Heat Deflection Temp. @ 264 PSI.....	169°F
Coefficient of Linear Expansion.....	3.30 x 10 ⁻⁵
Weight.....	49 lbs. per square
Warpage.....	0.00"
Heat Shrinkage.....	0.3%

Impact Resistance.....	Passes per ASTM D3679
Surface Distortion @ 140°F.....	0
Flame Spread Index.....	10
Fire Rating	Class A
Smoke Developed.....	395
Fuel Contribution.....	0
Average Time Of Burning.....	Self extinguished
Average Extent Of Burning.....	2.379mm
Weathering.....	Passes per ASTM D3679
Wind Load Rating*	200 + MPH

**(Wind Velocity based on IBC)*

Carrington Vinyl Siding passes or exceeds all industry standards per ASTM D3679.
 Made in the U.S.A. by America's dedicated workforce.
 Specifications subject to change without notice.

